

# Product Specification

## Cladseal EXT

Cladseal EXT is an elastomeric waterproofing strip based on the rubber polymer EPDM with a low water vapour transmission factor. The product is used as a vapour control layer such as façade waterproofing, damp proof course or similar. The product comes in black colour and has a surface texture on both sides for maximum adhesion. Cladseal EXT provide very long expected service life and is an environmental friendly product.



### Technical data

Thickness:	0.6/0.75/1.0/1.2/1.5 mm
Length:	25 m
Width:	Specified, from 100 to 1700 mm
Package:	Delivered stacked on pallets 1200x800 mm
Weight:	0.6 mm: 0.77 kg/m <sup>2</sup>
	0.75 mm: 0.97 kg/m <sup>2</sup>
	1.0 mm: 1.29 kg/m <sup>2</sup>
	1.2 mm: 1.55 kg/m <sup>2</sup>
	1.5 mm: 1.94 kg/m <sup>2</sup>
Sd-value:	0.6 mm: 19.2 m
	0.75 mm: 24 m
	1.0 mm: 32 m
	1.2 mm: 38,4 m
	1.5 mm: 48 m

### Physical properties

For detailed product data, please see corresponding Declaration of Performance.

### Storage

Store cool and dry in the original packaging. There are no limitations in shelf life.

### Approvals, Certificates & Specifications

CE EN 14909, CE EN 13984, ATG approval.



# Product Specification

## Paste Adhesive 3300

Adhesive based on synthetic rubber. Applied on substrate with standard type of a hand gun or a putty spade.

### Technical data

<b>Base:</b>	Adhesive based on synthetic rubber
<b>Colour:</b>	Black
<b>Flash point:</b>	<0°C
<b>Viscosity (at 20°C):</b>	4,500 ±2,000 Pa.s
<b>Solids:</b>	78 ±2 %
<b>Density (at 20°C):</b>	1,200 ±50 kg/m³
<b>Shelf life:</b>	9 months if stored cool in unopened original packing



### Package

600 ml/sausage  
12 pcs/box, 60 boxes/pallet

### Consumption/coverage

10-12 m/sausage

### Direction for use

Apply the adhesive in stripes onto the substrate with a cartridge gun, then, after a few minutes, place the strip onto the adhesive and press down firmly with a roller.

The maximum open time limit depends very much on the weather. In general, leaving things uncovered for a maximum of five minutes still produces satisfactory bonding. Bonding on warm substrates reduces the open time limit considerably!

When adhering vertically it may be necessary, depending on the weight of the strip, to detach it for a moment after applying the adhesive by pressing down the strip, then place it again and press down firmly (contact adhering).

The minimum processing temperature is + 5 °C.

### Suitable substrates

Paste Adhesive 3300 provides an excellent adhesion on many materials, such as EPDM/Butyl rubber, hard PVC, acrylic glass, SVS, RVS, stone, concrete, light weight concrete, lead, wood and bituminous substrates.

The substrates must be clean, free from oil and grease, and dry. Wet substrates or substrates covered with moisture must be dried before adhering. Dirty surfaces and tools may be cleaned with Cleaning Wash 9700.

### Warning

Paste Adhesive 3300 is inflammable. Avoid open flames or other sources of ignition.

Paste Adhesive 3300 is only suitable for by SealEco approved EPDM and Butyl membranes.

# Product Specification

## Contact Adhesive 5000

Contact Adhesive 5000 is a ready-for-use contact adhesive for adhering EPDM and Butyl membranes to dry substrates (such as wood, concrete and metals).

### Technical data

<b>Base:</b>	Synthetic rubber and synthetic resins, dissolved in inflammable organic solvents
<b>Colour:</b>	Black
<b>Flash point:</b>	Below 0°C
<b>Viscosity (at 20°C):</b>	2500 ±500 mPa.s
<b>Solids:</b>	41±2 %
<b>Density (at 20°C):</b>	865±10 kg/m³
<b>Shelf life:</b>	max. 12 month, provided that the glue is kept in a cool place in a well-sealed container



### Package

0.9 kg (1 litre)/can	12.5 kg (14.4 litre)/can
432 cans/pallet	33 cans/pallet
5.3 kg (6.1 litre)/can	25 kg (28.9 litre)/can
60 cans/pallet	24 cans/pallet

### Consumption/coverage

0.5 kg/m² (0,25kg/side)

### Direction for use

Contact Adhesive 5000 is ready for use but can if necessary be thinned with Cleaning Wash 9700 (max. 10 %) or toluene. Contact Adhesive 5000 must not be thinned or mixed with other products.

The adhesive must only be processed in dry weather conditions at temperatures of at least + 5 °C. The material and the base to be glued must also be dry and clean. Contact Adhesive 5000 should be applied with a stiff brush or a finely-toothed glue spatula. Contact Adhesive 5000 should be applied to both sides.

### Suitable substrates

Contact Adhesive 5000 provides an excellent adhesion on many materials, such as EPDM/Butyl rubber, hard PVC, acrylic glass, SVS, RVS, stone, concrete, light weight concrete, lead, wood and bituminous substrates.

The substrates must be clean, free from oil and grease, and dry. Wet substrates or substrates covered with moisture must be dried by means of hot air before adhering.

### Warning

Contact Adhesive 5000 is highly flammable. Keep away from open fire.

The solvents in Contact Adhesive 5000 are extremely harmful to polystyrene foam.

Contact Adhesive 5000 is only suitable for by SealEco approved EPDM and Butyl membranes.



# Product Specification

## Primer 9800

Polymer based primer for consequent use with self-adhesive rubber membranes.

### Technical data

<b>Base:</b>	Primer based on a synthetic rubber and synthetic resins, dissolved in inflammable organic solvents.
<b>Colour:</b>	Black
<b>Flash point:</b>	<0°C
<b>Viscosity (at 20°C):</b>	900 ±100 Pa.s
<b>Solids:</b>	36,3 %
<b>Density (at 20°C):</b>	840 ±10 kg/m³
<b>Shelf life:</b>	12 months if stored cool in unopened original packing.



### Package

1.0 litre/can

5.3 litre/can  
(60 cans/pallet)

6,30 litre/can

14,88 litre/can  
(33 cans/pallet)

### Consumption/coverage

175-250 g/m² depending on substrate.

### Direction for use

Primer 9800 is ready-for-use and must not be thinned or mixed with other products. The material and the substrate to be glued must be dry and clean. Primer 9800 should be applied in a thin even layer with a stiff brush or a finely-toothed spatula.

Primer 9800 may only be used in dry weather-conditions, no moisture must be enclosed between the primer-layer and the selfadhesive membrane.

Equipment and tools can be cleaned with Cleaning Wash 9700.

### Warning

Primer 9800 is highly flammable. Keep away from open fire.

Primer 9800 is not suitable as a primer for Polystyrene foam and plasticized PVC foil.